

Copyright © 2014 SETOX & IEPT, SASc.
This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/2.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

REVIEW ARTICLE

Ozone decomposition

Todor BATAKLIEV¹, Vladimir GEORGIEV¹, Metody ANACHKOV¹, Slavcho RAKOVSKY¹, Gennadi E. ZAIKOV^{2*}

¹ Institute of Catalysis, Bulgarian Academy of Sciences, Sofia, Bulgaria

² N.M. Emanuel Institute of Biochemical Physics, Russian Academy of Sciences, Moscow, Russia

* This join work is dedicated to the 80th Anniversary of Prof. Gennadi Zaikov

ITX070214R01 • Received: 23 February 2014 • Revised: 22 April 2014 • Accepted: 23 April 2014

ABSTRACT

Catalytic ozone decomposition is of great significance because ozone is a toxic substance commonly found or generated in human environments (aircraft cabins, offices with photocopiers, laser printers, sterilizers). Considerable work has been done on ozone decomposition reported in the literature. This review provides a comprehensive summary of the literature, concentrating on analysis of the physico-chemical properties, synthesis and catalytic decomposition of ozone. This is supplemented by a review on kinetics and catalyst characterization which ties together the previously reported results. Noble metals and oxides of transition metals have been found to be the most active substances for ozone decomposition. The high price of precious metals stimulated the use of metal oxide catalysts and particularly the catalysts based on manganese oxide. It has been determined that the kinetics of ozone decomposition is of first order importance. A mechanism of the reaction of catalytic ozone decomposition is discussed, based on detailed spectroscopic investigations of the catalytic surface, showing the existence of peroxide and superoxide surface intermediates.

KEY WORDS: ozone; catalysts; decomposition; synthesis; kinetics; mechanism

1. Introduction

In recent years, scientific research in all leading countries of the world has been aimed primarily at solving the deep environmental problems on the planet, including air pollution and global warming. One of the factors affecting negatively these processes is the presence of ozone in ground atmospheric layers. This is a result of the wide use of ozone in many important industrial processes, such as cleaning of potable water and soil, disinfection of plant and animal products, textile bleaching, complete oxidation of waste gases from the production of various organic chemicals, sterilization of medical supplies, *etc.* (Rakovsky *et al.*, 2007).

The history of ozone chemistry as a research field began immediately after its discovery by Schönbein in 1840 (Schönbein, 1840). The atmospheric ozone is found mainly in the so-called “ozone layer” at a height of 15 to 30 km above the earth surface wherein the ozone concentration ranges from 1 to 10 ppm (Wiley, 1991). The ozone

synthesis at that altitude runs photochemically through the influence of solar radiation on molecular oxygen. The atmospheric ozone is invaluable to all living organisms because it absorbs the harmful ultraviolet radiation from the sun. The study of the kinetics and mechanism of ozone reactions in modern science is closely related to solving the ozone holes problem, reflecting the trend of recent decades to the depletion of the atmospheric ozone layer.

Ozone has oxidation, antibacteriological and antiviral properties that make it widely used in the treatment of natural, industrial and polluted waters, swimming pools, contaminated gases, for medical use, *etc.* Catalytic decomposition of residual ozone is imperative because from environmental point of view the release of ozone in the lower atmosphere has negative consequences.

The presence of ozone in the surrounding human environment (airplane cabins, copiers, laser printers, sterilizers, *etc.*) also raises the issue of its catalytic decomposition as ozone is highly toxic above concentrations of 0.1 mg·m⁻³ (Razumovskii *et al.*, 1983; Brown *et al.*, 2002) and can damage human health. The use of catalysts based on transition metal oxides is emerging as very effective from an environmental perspective, providing at the same time a practical and inexpensive method for the decomposition of residual ozone.

Correspondence address:

Prof. Gennadi E. Zaikov, DSc.

N.M. Emanuel Institute of Biochemical Physics
Russian Academy of Sciences
Kosigina St. #4, Moscow 119334, Russia
E-MAIL: gezaikov@yahoo.com

2. Some physico-chemical properties of ozone

Ozone is an allotropic modification of oxygen that can exist in all three physical conditions. In normal conditions, ozone is a colorless gas with a pungent odor, while at very low concentrations (up to 0.04 ppm) it can give the feeling of pleasant freshness. A characteristic property of ozone odor is the fact that it is easily addictive and at the same time hazardous for people who work with ozone in view of its high toxicity at concentrations above the limit ($>0.1 \text{ mg}\cdot\text{m}^{-3}$).

When the ozone concentration exceeds 15–20% it has a blue color. At atmospheric pressure and temperature of 161.3 K, the ozone becomes fluid and is of deep blue color. It cures at 80.6 K by acquiring a dark purple color (Lunin *et al.*, 1998). Ozone is explosive in all three physical conditions. Work with ozone concentrations of 0 to 15% can be considered safe (Razumovskii *et al.*, 1983). The danger of ozone explosion is a function of its thermodynamic instability ($\Delta G^{\circ}298 = -163 \text{ kJ}\cdot\text{mol}^{-1}$) and ozone decomposition to diatomic oxygen is a thermodynamically favorable process with heat of reaction $\Delta H^{\circ}298 = -138 \text{ kJ}\cdot\text{mol}^{-1}$ (Perry & Green, 1997). The ozone molecule consists of three oxygen atoms located at the vertices of an obtuse-angled triangle with a central angle of $116^{\circ}8' \pm 5'$ and length of O–O-bond: $\rho_{\text{O-O}} = 0.1278 \pm 0.0003 \text{ nm}$ (Figure 1).

In gas phase, the ozone molecule is a singlet biradical while in liquid phase it reacts generally as a dipolar ion. The homogeneous reaction of pure gaseous ozone decomposition is characterized by a certain velocity at sufficiently high temperatures. The kinetics study of ozone thermal decomposition is also complicated by the fact that above a certain critical temperature the steady kinetic decomposition is transformed into explosion, subsequently passing to detonation (Rakovsky *et al.*, 2007). According to Thorp (1955), ozone detonation is observed above 105°C . The gaseous ozone is characterized by different times of half-life, depending on the temperature (Table 1).

The ozone structure is resonance stabilized, which is one of the reasons for its resistance against decomposition at low temperatures (Figure 2).



In most reactions with inorganic compounds, ozone reacts with participation of one atom oxygen and the other two are separate as O_2 . Typically, the elements are oxidized to their highest oxidation states. For example, manganese is oxidized to $[\text{MnO}]^{4-}$, halogen oxides to metals (ClO_2 , Br_2O_5), ammonia to NH_4NO_3 , nitrogen

oxides pass into N_2O_5 (Kutsuna *et al.*, 1994; Naydenov *et al.*, 1995; Rakitskaya *et al.*, 1994).

Ozone has spectral characteristics from the IR-region to the vacuum UV-region, which are present in a significant number of works as the majority of them are carried out with gaseous ozone (Tanaka *et al.*, 1953; De More & Paper, 1964; Beitker & Schurath, 1974; Inn & Tanaka, 1953; Griggs, 1968; Taube, 1957; Galimova *et al.*, 1973). It should be noted that most researchers who use the spectrophotometric method for analysis of ozone work in the main area of the spectrum $200\div 310 \text{ nm}$, where is the wide band with a maximum at $\sim 255 \text{ nm}$ for gaseous ozone (De More & Paper, 1964; Inn & Tanaka, 1953; Griggs, 1968; Taube, 1957). That maximum is characterized with a high value of the coefficient of extinction (Table 2).

3. Ozone synthesis and analysis

Ozone for industrial aims is synthesized from pure oxygen by thermal, photochemical, chemical, electrochemical methods, in all forms of electrical discharge and under the action of a particle stream (Rakovsky *et al.*, 2007). The synthesis of ozone is carried out by the following reactions shown in the scheme:





where: M is every third particle.

At low temperatures, the gas consists essentially of molecular oxygen and at higher by atomic oxygen. There is no area of temperatures at normal pressure wherein the partial pressure of ozone is significant. The maximum


Table 1. Half-life of ozone.

Temp. ($^{\circ}\text{C}$)	Half-life
-50	3-months
-35	18-days
-25	8-days
20	3-days
120	1.5-hours
250	1.5-seconds




steady-state pressure which is observed at the temperature of 350 K is only 9.10^{-7} bar. The values of the equilibrium constant of reaction (2) at different temperatures are presented in Table 3 (Hon & Yan, 1993).

At high temperatures, when the concentration of atomic oxygen is high, the equilibrium of reaction (2) is moved to the left and the ozone concentration is low. At low temperatures, the equilibrium is shifted to the right, but through the low concentration of atomic oxygen the ozone content is negligible. For synthesis of significant concentrations of ozone it is necessary to combine two following conditions: 1) low temperature and 2) the formation of superequilibrium concentrations of atomic oxygen. It is possible to synthesize superequilibrium atomic concentrations of oxygen at low temperatures by using non-thermal processes, such as dissociation of oxygen with particle flow, electrons, $h\nu$, electrochemical and chemical influences. At low temperatures, ozone will always be formed when there is a process of oxygen dissociation. Higher concentrations of ozone may be obtained by thermal methods providing storage ("quenching") of superequilibrium concentrations of atomic oxygen at low temperatures. Photochemical synthesis of ozone occurs upon irradiation of gaseous or liquid oxygen by UV radiation with the wavelength $\lambda < 210$ nm (Deninno & McCarthy, 1997). It is assumed, that the formation of ozone in the presence of radiation with a wavelength in the range of $175 < \lambda < 210$ to be associated with the formation of excited oxygen molecules (Claudia *et al.*, 1994):



The photochemical generation of ozone has an important role in atmospheric processes, yet it is hard to apply for industrial application because of the high energy costs

(32 kWh.kg⁻¹ ozone) for the preparation of high-energy shortwave radiation. Nowadays the industrial synthesis of ozone happens mainly by any of the electric discharge methods by passing oxygen containing gas through high-voltage (8–10 kV) electrodes. The aim is creation of conditions in which oxygen is dissociated into atoms. This is possible in all forms of electrical discharges: smoldering, silent, crown, arc, barrier, *etc.* The main reason for the oxygen dissociation is the hit of molecular oxygen with electrons accelerated in the electric field (Rakovsky *et al.*, 2007; Lunin *et al.*, 1998), when part of the kinetic energy is transformed in energy of dissociation of the bond O–O and excitation of oxygen molecules. In general, molecule oxygen dissociates in two oxygen atoms, then in the final stage two molecules of oxygen form one oxygen atom and one ozone molecule:



Technically, the synthesis of ozone is carried out in discharge tubes – ozonators. One of the most commonly used type of tubes are Siemens ozonators (Figure 3).

This ozonator represents two coaxial pipes brazed one to another, supported inside of the inner side and outside of the outer side with electrically conductive coating of aluminum, silver, copper and the like. It is submitted to high voltage up to 20 kV and dry and pure oxygen is left to pass through the ozonator. The ozone is synthesized on the other end of the ozonator. Ozone concentration depends on the parameters of the current – voltage, frequency and power properties of the ozonator – thickness, length and type of glass tube, the distance between the electrodes and temperature. The ozone concentration depends on the current parameters – voltage, frequency and power, on the properties of the ozonator – thickness,

Table 2. Coefficient of extinction (ϵ , L.mol⁻¹.cm⁻¹) of gaseous ozone in UV-region (Alexandrov *et al.*, 1983)

λ , nm	(Kondratev, 1990)	(Vupputuri, 1988)	(Heisig <i>et al.</i> , 1997)	(Emelyanova <i>et al.</i> , 1965)
253.6*	2981	3024	2952	3316
270	-	-	-	2302
289.4	383	337.5	387.5	-
296.7**	150.5	153.4	156.8	-
302.2	74.4	-	74.4	-
334.2	1.50	-	1.46	-

* The values of ϵ are 1830 L.mol⁻¹.cm⁻¹ at 254.0 nm (Razumovskii *et al.*, 1983) and 3020 L.mol⁻¹.cm⁻¹ at 253.6 nm (Beitker & Schurath, 1974)

** $\epsilon = 160$ L.mol⁻¹.cm⁻¹ at 295 nm (Galimova *et al.*, 1973)

Table 3. Equilibrium constant (K_e) of reaction (2) depending on the temperature.

T, K	1500	2000	3000	4000	5000	6000
K_e , M	$1.662 \cdot 10^{-11}$	$4.413 \cdot 10^{-7}$	$1.264 \cdot 10^{-2}$	2.104	48.37	382.9




Figure 3. Principal scheme of Siemens ozonator.

length and type of glass tube, on the distance between the electrodes, and also on the temperature.

The analysis of ozone concentration is developed by various physical and chemical methods discussed in detail in the monograph (Razumovskii & Zaikov, 1974). It should be noted that preference is given to the spectrophotometric method compared with the iodometric method, determined by the lack of need of continuous pH monitoring during ozone analysis and also by the possibility of direct observation of the inlet and outlet ozone concentrations in the system, allowing precise fixing of the experimental time and its parameters. For determination of the ozone amount not absolute values of concentration but rather ratios of the proportional values of optical densities can be used, excluding the error influence at expense of the inaccuracy in calibration of the instrument.

4. Ozone decomposition

The reaction of ozone on the surface of solids is of interest from different points of view. Along with the known gas cycles depleting the atmospheric ozone, a definitive role is played also by its decomposition on aerosols, so that quantity is growing at the expense of the anthropogenic factor. The growth of ozone used in chemical industries set up the task for decomposition of the residual ozone on heterogeneous, environmentally friendly catalysts. In humid environments and under certain temperatures and gas flow rates this subject has not yet been entirely understood.

4.1. Stratospheric ozone

The importance of the stratospheric ozone is determined by its optical properties – its ability to absorb the UV solar radiation with a wavelength of 220 to 300 nm. The absorption spectrum of ozone in the ultraviolet and visible region is given in Figure 4.

The main absorption band in the name of Hartley is in the range of 200–300 nm with a maximum at the





Figure 4. UV-absorption spectrum of O₃ with maximum at 254 nm.







wavelength of 254 nm. The stratospheric ozone layer has a thickness of 3 mm and its ability to absorb UV rays protects the earth's surface of biologically active solar radiation which destroys the most important biological components, proteins and nucleic acids.

The fundamentals of the photochemical theory of stratospheric ozone were given by the English chemist Chapman (1930a,b), according to whom the photochemical decomposition of ozone occurs by the following reactions:



The proposed mechanism leads to formation of oxygen atoms in ground and excited state. This cycle of decomposition is called the cycle of "residual oxygen". The photodissociation of ozone (11, 12) takes place under the action of solar radiation with a wavelength of less than 1134 nm. Decomposition of ozone following these reactions (11, 12) can be observed at any altitude near to ground level. The photochemical synthesis of ozone in the stratosphere requires its degradation in reaction (10). Following this reaction, 20% of the stratospheric ozone was found to decompose (Johnston, 1975). The effect of the ozone layer on climate changes is related to the absorption of radiation which occurs not only in the UV-region but also in the IR-region of the spectrum. By absorbing IR rays from the Earth's surface, ozone enhances the greenhouse effect in the atmosphere (Watson *et al.*, 1986; Gerchenson *et al.*, 1990). The connection of this problem with the climate is extremely complicated due to the variety of physical and chemical factors that influence the amount of atmospheric ozone (Johnston, 1975).

The destruction of ozone in the atmosphere is linked to catalytic cycles of the type:



where: X is OH, NO or Cl, formed by dissociation of freons in the atmosphere (Crutzen & Smalcel, 1983).

The stratospheric cycles of ozone decomposition have been discussed in several works but fundamental contributions have been made particularly by Johnston (1975) and Farnen *et al.* (1985). The effective action of the molecules-catalysts in the cycles of ozone decomposition is determined by their concentrations in the atmosphere, which depends on the rates of regeneration and exit from the respective cycle (Solomon *et al.*, 1986). The ratio between the rate of decomposition of residual oxygen and the rate of catalyst outgoing from the cycle determines the length of the chain reaction and corresponds to the number of O₃ molecules destroyed by one catalytic molecule. The number of stages of ozone decomposition in a single catalytic center can reach 106 (Rakovsky *et al.*, 2007). The


reduction of the ozone amount over Antarctica, *i.e.* the thinning of the ozone layer, is mainly due to the action of the chlorine cycle (Vupputuri, 1988; Kondratev, 1989; 1990). During this catalytic cycle, the presence of one chlorine atom in the stratosphere can cause the decomposition of 100000 ozone molecules.

4.2. Catalysts for decomposition of ozone

The use of ozone for industrial aims is related to the application of effective catalysts for its decomposition, since as already mentioned, the release of ozone in the atmosphere near ground level is dangerous and contaminates the air (Rakovsky *et al.*, 2007; Heisig *et al.*, 1997; Rakitskaya *et al.*, 2001). Ozone has a great number of advantages as an oxidizing agent and in that capacity it has been used in different scientific investigations concerned with neutralization of organic contaminants (Skoumal *et al.*, 2006; Bianchi *et al.*, 2006), as in the presence of a catalyst the ozonation efficiency increases (Ma *et al.*, 2004; Zhao *et al.*, 2008). Due to its antibacterial and antiviral properties, ozone is one of most used agents in water treatment (Von Gunten, 2003). This fact results in a considerable interest of researchers to study homogeneous and heterogeneous reactions of ozone decomposition, as well as the participation of ozone in multiple oxidation processes.

4.2.1. Ozone decomposition on the surface of metals and metal oxides

The first studies on the catalytic decomposition of gaseous ozone (Monhot, 1907) showed that the degradation of ozone is accelerated in the presence of Pt, Pd, Ru, Cu, W, *etc.* The catalytic activity of metals in the decomposition of ozone was studied by Kashtanov *et al.* (1936) highlighting that silver (Ag) showed a higher catalytic activity compared to copper (Cu), palladium (Pd), and tin (Sn). From earlier works on the decomposition of ozone, the study of Schwab (Schwab & Hartmann, 1964) should be noted. They investigated catalysts based on metals from the I–IV group and their oxides in different oxidation levels and they found that the catalytic activity of these oxides increased with the increase in the oxidation state of the metal. Below the relationship is presented which exists between the catalytic activity degree of a number of elements and their oxides in the reaction of catalytic decomposition of ozone:




These results can be explained by the higher activity of the ions of the respective elements relative to the activity of the elements themselves, as well as the importance of ionic charge in the catalytic reaction. Further early studies were presented by Emelyanova *et al.* (Emelyanova *et al.*, 1964; Emelyanova *et al.*, 1965; Emelyanova & Strakhov, 1968) discussing catalytic decomposition of gaseous ozone at temperatures from -80°C to $+80^\circ\text{C}$ and an ozone concentration of 8.8 vol.%. As catalysts elements of the platinum group were used: Pt, colloidal Pt, Pd, Ir and colloidal Ru, NiO, and Ni_2O_3 . Experiments were

carried out in a tube reactor at a gas velocity of $5\text{L}\cdot\text{h}^{-1}$. The studies indicated an identical activity of the nickel oxide and colloidal platinum at temperatures from 20°C to 80°C . At -80°C , the activity of the nickel oxide fell to zero, while the platinum remained active. This is related to the low activation energy of decomposition of O_3 on the metal surface ($\sim 1\text{ kcal}\cdot\text{mol}^{-1}$). Further it was found that the process of decomposition of ozone in the presence of colloidal Rh and Ir at $+3^\circ\text{C}$ and $+20^\circ\text{C}$ slowed down after four hours, and the catalysts lost activity. Sudak and Volfson's silver-manganese catalyst (Sudak & Volfson, 1983) for the decomposition of ozone was used at low temperatures in different gas mixtures. Commercial reactors operating with this catalyst have a long life of performance and maintain a constant catalytic activity. The preparation of other high performance metal catalysts for the decomposition of ozone, including the development of special technology for synthesis, determination of the chemical composition, experimental conditions and catalytic activity were presented in a number of studies by Japanese authors published in the patent literature (Hata *et al.*, 1988; Tchiyara, 1988; Kobayashi *et al.*, 1988; Terui *et al.*, 1990; Terui *et al.*, 1991; Oohachi *et al.*, 1993; Kobayashi & Mitsui, 1988; Kuwabara & Fujita, 1991; Hata *et al.*, 1987; Terui *et al.*, 1990; Yoshimoto *et al.*, 1990). The main metals used were Pt, Pd, Rh and Ce, as well as metals and metal oxides of Mn, Co, Fe, Ni, Zn, Ag and Cu. The high price of precious metals stimulates the use of metal oxide catalyst supporters with a highly specific surface such as $\gamma\text{-Al}_2\text{O}_3$, SiO_2 , TiO_2 , ZrO_2 and charcoal. Hata *et al.* (1988) synthesized a catalyst containing 2% Pt as active component on a supporter composed of a mixture of 5% SiO_2 and 95% $\gamma\text{-Al}_2\text{O}_3$ having a specific surface area of $120\text{m}^2\cdot\text{g}^{-1}$. They impregnated chloroplatinic acid onto the carrier at 80°C , then the sample was dried successively at 120°C and 400°C and atmospheric pressure. At an operating temperature of 20°C , the gas velocity of 20000h^{-1} and 10 ppm initial concentration of ozone in the fed gas, this catalyst shows 95% catalytic activity. Another catalyst comprising TiO_2 , SiO_2 and Pt (Kobayashi *et al.*, 1988) degrades 94, 97 and 99% of the ozone in the air stream at temperatures of 20, 50 and 100°C respectively. Therui *et al.* (1991) deposited the metals Mn, Co, Fe, Ni, Zn, Ag or their oxides in the weight ratio with regard to the carrier in the range of 0 to 60%, as well as Pt, Pd and Rh of the 0 to 10 wt %, and also mixed oxides such as $\text{TiO}_2\text{-SiO}_2$, $\text{TiO}_2\text{-ZrO}_2$ and $\text{TiO}_2\text{-SiO}_2\text{-ZrO}_2$, supported on colloidal polyurethane with $400\text{m}^2\cdot\text{g}^{-1}$ specific surface. The catalysts were placed in tube reactors and their catalytic activity, measured in the decomposition of ozone at a concentration of 0.2 ppm, was 99%. In published patents, various precursors and methods for synthesis were used for catalysts with identical chemical composition. For example, TiO_2 and MnO_2 (Kobayashi & Mitsui, 1988) were obtained from aqueous solutions of $\text{H}_2\text{SO}_4 + \text{TiOSO}_4$ and $\text{Mn}(\text{NO}_3)_2\cdot 6\text{H}_2\text{O}$, while in another case (Kuwabara & Fujita, 1991), TiO_2 was purchased from the manufacturer, and the MnO_2 was prepared by precipitation of aqueous solutions of MnSO_4 and NH_3

in an atmosphere of oxygen followed by calcination. The application of the proposed system conditions makes it possible to assess the effectiveness of the catalysts and may be used for development of new catalytic systems. Many of the catalysts operate at ambient temperatures (293–323 K), high space velocities (>20000 h⁻¹), and exhibit high catalytic activity (conversion 95%). In recent years, more and more researchers have focused on the development, study and application of catalysts for decomposition of ozone based on supported or native metal oxides, with regard to the already mentioned fact – the high price of metals of the platinum group. In recent years, more and more researchers have focused on the development, study and application of catalysts for decomposition of ozone based on supported or unsupported metal oxides, due to the already mentioned fact – the high price of metals of the platinum group. In this respect, the most widely used are the oxides of Mn, Co, Cu, Fe, Ni, Si, Ti, Zr, Ag and Al (Oyama, 2000; Einaga & Futamura, 2004; Tong *et al.*, 2003; Konova *et al.*, 2006; Stoyanova *et al.*, 2006; Popovich *et al.*, 1985; Popovich, 1988; Radhakrishnan *et al.*, 2001; Zavadskii *et al.*, 2002). It has been found that the oxides of transition metals were found to exhibit the highest catalytic activity in the decomposition of ozone (Imamura *et al.*, 1991), particularly the catalysts based on manganese oxide (Dhandapani & Oyama, 1997). Manganese oxide is used as a catalyst for various chemical reactions including the decomposition of nitrous oxide (Lo Jacono & Schiavello, 1976; Yamashita & Vannice, 1996; Ma *et al.*, 1995) and isopropanol (Ma *et al.*, 1995; Ma *et al.*, 1995), oxidation of methanol (Baltanas *et al.*, 1986), ethanol (Li & Oyama, 1996), benzene (Naydenov & Mehandjiev, 1993; Einaga & Ogata, 2009), CO (Ma *et al.*, 1995; Ma *et al.*, 1995; Boreskov, 1965) and propane (Baldi *et al.*, 1998) as well as for reduction of nitric oxide (Kapteijn *et al.*, 1994) and nitrobenzene (Maltha *et al.*, 1994). In terms of technology for the control of air pollution, manganese oxides are used both in the decomposition of residual ozone and the degradation of volatile organic compounds (Hunter & Oyama, 2000; Subrahmanyam *et al.*, 2007). Oxides of Mn, Co, Ni, Cr, Ag, Cu, Ce, Fe, V and Mo supported on γ -Al₂O₃ on cordierite foam (60 pores per cm and geometry 5.1 × 5.1 × 1.3 cm) have been prepared and tested in the reaction of decomposition of ozone (Dhandapani & Oyama, 1997). Experiments were carried out at a temperature of 313 K, a linear velocity of 0.7 m.s⁻¹, inlet ozone concentration of 2 ppm, a relative humidity of 40% and a total gas flow rate of 1800 cm³.s⁻¹. The catalyst activity was found to decrease over time and the measurements were made only when the speed of decomposition was stabilized. After comparison of the conversion degree of ozone, conclusions on their catalytic activity were drawn and they were arranged as follows: MnO₂ (42%) > Co₃O₄ (39%) > NiO (35%) > Fe₂O₃ (24%) > Ag₂O (21%) > Cr₂O₃ (18%) > CeO₂ (11%) > MgO (8%) > V₂O₅ (8%) > CuO (5%) > MoO₃ (4%). The high dispersibility of the material was confirmed by X-ray diffraction analysis. TPR profile of supported and unsupported MnO₂ was done. It was found that the reduction temperature of the supported MnO₂,

Co₃O₄, NiO, MoO₃, V₂O₅ and Fe₂O₃ was in the range of 611–735 K, while that of CeO₂ was above 1000 K. Of all the examined metal oxide samples, MnO₂ had the lowest reduction temperature and exhibited a higher reduction ability in comparison with the others. On the basis of experiments, the mechanism of decomposition of ozone on the catalytic surface was proposed, including the formation of intermediate ionic particles possessing either superoxide or peroxide futures:



where * denotes active center.

A distinguishing peculiarity of the proposed scheme is the assumption that the key intermediate particle ^{*}O₂ is not desorbed immediately. This can happen if it has a partial ionic character (O²⁻, O₂²⁻). The catalytic activity of iron oxide Fe₂O₃ in decomposition of ozone was studied also in earlier work of Rubashov (Rubashov *et al.*, 1972; Rubashov & Strahov, 1973). Fe₂O₃ was found to show a catalytic activity only when used in the form of particles with small diameter, while the catalyst consisting of aggregated particles was not efficient. Furthermore, the stability of the catalyst was not high and its poisoning was due to the formation of oxygen directly associated with the surface. Reactivation of the catalyst was accomplished by subjecting it to vacuum thermal treatment to remove oxygen. The same catalyst was also studied in terms of the fluidized bed, wherein the rate constant for the catalytic reaction is higher than in the normal gas flow. By determining the constant of the decomposition of ozone on the surface of Fe₂O₃ at various temperatures, the activation energy of the process: E=(12.5±1) kcal.mol⁻¹ can be calculated. This value differs from that calculated by Schwab (Schwab & Hartmann, 1964) which is of the order of 2–3 kcal.mol⁻¹. The difference can be explained by the regimen in which the process is carried out: kinetic, in the first case, and diffusion in the second. Ellis & Tomets (1972) investigated the activity of 35 different materials with respect to decomposition of ozone and nickel oxide and charcoal turned out to be the best catalysts. Measurements were carried out at room temperature, gas velocities between 250–2000 L.h⁻¹, atmospheric pressure and ozone concentrations (1.1–25) × 10¹² molecules per cm³. The measured rate of decomposition of ozone corresponds to a first order reaction. The authors ignoring the decomposition of ozone in the bulk proposed a homogeneous decomposition on the surface:



In this case “M” is an active center on the surface which reduces the energy of activation of the reaction and accelerates decomposition. Assuming that the portion of the surface area occupied by ozone θ is proportional to the

partial pressure of ozone in the volume, the kinetic region of ozone leaving from the gas phase is equal to:

$$-\frac{dp_{O_3}}{dt} = k\theta = k'p_{O_3} \quad (18)$$


It is obvious that a first order of reaction with respect to the decomposition of ozone has been established, which has been confirmed experimentally. The decomposition of ozone in gradient-free reactor is considered in the work (Houzellot & Villermaux, 1976). As a catalyst a thin film of nickel oxide coated on the walls of the reactor was used. Turbulence of gas flow in such a type of reactor would avoid the physical transfer and provide conditions for studying the kinetics only on the catalytic surface. In this case, the turbulent diffusion is superior to the rate of reaction and the process is conducted in the kinetic regimen. The rate constant in the range of 10–40 °C is calculated by the expression:

$$k = 10^{2.54} p^{-0.5} \exp(-1250/T) \text{ cm/s} \quad (19)$$

where p is in atm.

Experiments made with different pressures of the oxygen and ozone-helium mixtures showed that the rate constant changes depend on the total pressure and not on the partial pressure of ozone. Hence the authors have concluded that the catalyst operates in inner diffusion mode, *i.e.* the reaction rate is limited by molecular diffusion in the pores of the catalyst. These and other assumptions made it possible to explain the resulting experimental dependence of the rate constant on the total pressure of the mixture in the gas phase. The kinetics of decomposition of ozone in gradient-free reactor was investigated in the work (Tarunin *et al.*, 1981). It measured activities of $\gamma\text{-Al}_2\text{O}_3$, hopkalite (MnO_2 , CuO , bentonite), silver-manganese oxide, alumina-palladium and alumina-platinum catalysts. The experiments were conducted at 60 °C and initial ozone concentration of $2.7 \times 10^{-5} \text{ mol.L}^{-1}$. The most active of the catalysts tested turned out to be silver-manganese oxide and hopkalite. The kinetics of decomposition of ozone has been determined to be of first order. The rate constants and energies of activation were also defined, the latter fluctuating in the range of 6–10 kcal.mol^{-1} . Of interest are conclusions of authors on the active surface of the catalyst. The activation energy was found not to depend on the dispersibility, but influencing the catalytic activity. On the other hand, dispersibility did not increase the inner surface of the porous material. Hence it has been concluded that the decomposition of ozone occurs in the outer kinetic region, *i.e.* the heterogeneous reaction is limited mainly by the outer surface of the catalyst. During the study of the decomposition of ozone in the presence of nickel oxide (Rakovsky *et al.*, 1979) it was established that the reaction was of first order. It has been proposed that the limiting stage is the adsorption of ozone to the catalytic surface. The EPR spectra revealed the presence of ozonide ion radical O_3^- (Che & Tench, 1982; Tench & Lawson, 1970). The formation of O_3^- is explained by the

process of electron transfer from the catalyst to the ozone, so that the surface Ni^{2+} ions are oxidized to Ni^{3+} . Further studies of the authors showed that in this way approximately 5% of the total reaction took place. The remaining amount of the ozone was decomposed by molecular mechanism:



In some cases, the ozone does not remain in the molecular state and dissociates to atomic or diatomic oxygen species. Ozonide particles on catalytic surface are generated by the reaction:



Figure 5 shows the characteristic bands of the EPR spectrum at $g_1 = 2.0147$, $g_2 = 2.0120$ and $g_3 = 2.0018$, due to the formation of the ion-radical O_3^- .

Martinov *et al.* (1994) studied the influence of the CuO , CoO and NiO on the process of ozone decomposition. The catalysts were prepared using aqueous solutions of the respective nitrates and were supported on the walls of the tubular reactor ($l=25 \text{ cm}$, $D=1.6 \text{ cm}$). The reactor was heated to 370 °C for 5 hours, after which each of the catalysts was treated with ozone at a concentration of 0.5 vol. % for 6 hours at a gas velocity of 100 L.h^{-1} . After solving the diffusion-kinetic equation of the ozone decomposition reaction, the diffusion and the kinetic constants can be defined as well as the coefficients of ozone decomposition. These characterize the decomposition rate of ozone molecules on the catalyst surface toward the rate of the hits of molecules with the surface. The results of these calculations for different samples are presented in Table 4, wherein ω is space velocity, γ -coefficient of ozone decomposition and k_{exp} , k_{kin} are respectively experimental and theoretical rate constants.




Figure 5. EPR spectrum of O_3^- at a temperature 77 K.

Table 4. Kinetic parameters of the reaction of ozone decomposition on some oxides.

Catalyst	w, l/h	k_{exp} , s ⁻¹	$g \cdot 10^{-5}$	k_{kin} , s ⁻¹
CuO	20	1.0	4.8	2.8
CoO	100	0.9	4.1	2.4
CoO	200	1.3	6.3	3.6
NiO	20	0.9	4.4	2.6
NiO	100	1.0	4.8	2.8
NiO	200	1.7	8.1	4.4

Table 5. Densities of active centers and specific surfaces.




Catalyst	S_g , m ² ·g ⁻¹	density, mmol·g ⁻¹ (O ₂ /O ₃ TPD)	dispersion, %
MnO _x /Al ₂ O ₃	92	40	12
MnO _x /ZrO ₂	45	163	47
MnO _x /TiO ₂	47	31	9
MnO _x /SiO ₂	88	13	4

It is evident that the activity of the catalysts increases at $\omega=200$ L·h⁻¹. This is explained by the flow of catalytic reaction between kinetic and diffusion regions. Furthermore, the values of the rate constants of ozone decomposition in kinetic mode are almost 3 times higher than the experimental ones.

Radhakrishnan *et al.* (2001) used manganese oxide catalysts supported on Al₂O₃, ZrO₂, TiO₂ and SiO₂ for studying the support influence on the kinetics of decomposition of ozone. By using different physical methods of analysis, such as “*in situ*” laser Raman spectroscopy, temperature-programed desorption of oxygen and measuring of specific surface area (BET), the manganese oxide was found to be highly dispersed on the support surface. The Raman spectra of the supported catalysts revealed the presence of Mn-O bands as the result of well dispersed manganese oxide particles on the Al₂O₃ and SiO₂ supported catalysts. During the process of ozone decomposition on the catalytic surface, a signal from adsorbed particles appears at Raman spectra in the region of 876–880 cm⁻¹. These particles were identified as oxygen particles from peroxide type (O₂²⁻), which disappeared upon catalyst heating to 500 K. Using temperature-programed desorption of oxygen, the number of active manganese centers on the catalyst surface is calculated. After integration of the TPD peaks area corresponding to desorption of adsorbed oxygen, besides the density of active sites also the corresponding dispersion values of the catalysts are identified. These results, as the calculated specific surface areas of the catalytic samples, are shown in Table 5. The catalysts were tested in reaction of ozone decomposition to determine their activity, and it was found that the rate of decomposition increased with increasing the ozone partial pressure and temperature. The kinetic parameters of the reaction were calculated. The activation energy was in the range of 3–15 kJ·mol⁻¹,

depending on the catalyst sample, as it is lower (3 kJ·mol⁻¹) in the case of ozone decomposition on MnO_x/Al₂O₃. This may be related to the structure of this catalyst which was the only one of the samples tested with a mononuclear manganese center coordinated by five oxygen atoms, as demonstrated on using absorption fine-structure X-ray spectroscopy. The same method revealed that the other three supported catalysts possessed multi-core active manganese centers surrounded as well by five oxygen atoms.

A mechanism of ozone decomposition on MnO_x/Al₂O₃ catalyst has been proposed:



The presented mechanism consists of electronic transfer from the manganese center to ozone, followed by reduction of manganese by desorption of peroxide particles to form oxygen (O₂²⁻ → O₂ + 2e⁻).

A study of MnO_x/Al₂O₃ with absorption fine-structure X-ray spectroscopy is presented also in publication (Einaga *et al.*, 2005). The aim of the work was to receive important information on the catalytic properties of the supported manganese oxides in oxidation reactions using ozone. The structural changes in the manganese oxide supported on alumina were detected in the process of catalytic ozone decomposition at room temperature. It was found that during the ozone decomposition in the presence of water vapor, the manganese was oxidized to a higher oxidation state. At the same time the water molecule combined to manganese active center due to cleavage of the Mn-O-Al bond. The catalyst was completely regenerated after calcination in oxygen at 723 K.

The paper (Martinov *et al.*, 1999) studied the influence of nickel oxide addition on the activity of cement containing catalyst for ozone decomposition. The activity of the samples was measured by calculating the rate of decomposition γ which shows the degree of active interactions (leading to decomposition) of ozone molecules with catalytic surface. According to Lunin *et al.* (1998), the expression for γ is:

$$\gamma = \frac{4\omega \cdot \ln(C_0 / C)}{V_t \cdot S} \quad (25)$$

where: V_t - specific heat velocity of ozone molecules; S - geometric surface of the catalyst; ω - space velocity of the gas stream; C_0 and C - inlet and outlet ozone concentrations.

Addition of nickel oxide to the catalyst composition improved its catalytic properties. Upon decomposition of wet ozone, a decrease in the activity of all samples tested was found, as the calculated values for γ were 2–3 times lower compared with the value obtained after decomposition of dry ozone. On the basis of the values measured for energy of activation ($E_a = 5.9 \pm 0.3$ kJ·mol⁻¹) of ozone decomposition in the region of high

temperatures (300–400 K), and the corresponding values of E_a ($15.2 \pm 0.4 \text{ kJ} \cdot \text{mol}^{-1}$) in the region of low temperatures, the conclusion was drawn that in the first case the process went to the outer diffusion region, whereas in the second into the inner diffusion region. The factor of diffusion suspension or the accessible part of the surface is estimated to elucidate the role of the internal catalytic surface. This permitted the calculation that at room temperature the molecules of ozone enter into the pores of the catalyst at a distance not greater than $\sim 10^{-4} \text{ cm}$.

Lin *et al.* [97] studied the activity of a series of oxide supports and supported metal catalysts with respect to decomposition of ozone in water. Tested in reaction conditions, activated carbon showed a relatively high activity, while the zeolite support (HY and modernite), Al_2O_3 , SiO_2 , $\text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ and TiO_2 showed zero or negligible activity. Of all the supported metal catalysts submitted to ozone dissolved in water, the noble metals had the highest activity in ozone decomposition, except gold. The metals are deposited on four types of supports (Al_2O_3 , SiO_2 , $\text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ and TiO_2). The highest activity was measured for the catalysts deposited on silica. Of all the samples tested, the catalyst containing 3% Pd/ SiO_2 was found to be the most effective in the reaction of ozone decomposition. A comparison of some indicators for Pd catalysts deposited on different supports is presented in Table 6.

It was determined as the first order of reaction of ozone decomposition on 3% Pd/ SiO_2 regarding the concentration of ozone. In the presence of the same catalyst, the calculated activation energy was about $3 \text{ kcal} \cdot \text{mol}^{-1}$ and it is assumed that the reaction proceeds in the diffusion region. The proposed mechanism of catalytic decomposition of ozone in water is similar to the mechanism of decomposition of gaseous ozone. Table 7 shows two possible reaction pathways of ozone decomposition on metals or oxides, depending on the fact whether oxygen is adsorbed on the catalytic surface.

The literature provides also data for the study of ozone decomposition in water in the presence of aluminum (hydroxyl) oxide (Qi *et al.*, 2008). It has been suggested that the surface hydroxyl groups and the acid-basic properties of aluminum (hydroxyl) oxides play an important role in catalytic decomposition of ozone.

The environmental application of ozone in catalysis was demonstrated in article (Rosal *et al.*, 2008), devoted to the ozonation of naproxen and carbamazepine on titanium dioxide. The experiments were carried out in aqueous solution at $T = 25^\circ\text{C}$ and in pH range of 3–7. The results indicated that naproxen and carbamazepine are completely destructed in the first few minutes of the reaction. The degree of mineralization during the non-catalytic reaction flow was measured to be about 50%, formed primarily in the first 10–20 minutes. The presence of the catalyst increased to more than 75% the degree of mineralization of the initial hydrocarbon. Furthermore, it was found that the catalyst increased the mineralization in both acid and neutral solution, as the best results were obtained at slightly acidic media. This effect may be related with a possible adsorption of

intermediate reaction products on Lewis acidic catalytic sites. The titanium dioxide possibly catalyzes the ozone decomposition in acidic media, whereas in neutral solution the ozone destruction is inhibited. This precluded the flow of mechanism based on surface formation of hydroxyl radicals followed by their migration and complete reaction with the organic compounds. The variation of the quantity of total organic carbon is modeled as a function of the integral of the applied amount of ozone. On this basis, it is assumed that the reaction between organic compounds and ozone is of second order. The calculated pseudo homogeneous catalytic rate constants are $7.76 \times 10^{-3} \pm 3.9 \times 10^{-4}$ and $4.25 \times 10^{-3} \pm 9.7 \times 10^{-4} \text{ L} \cdot \text{mmol}^{-1} \cdot \text{s}^{-1}$ for naproxen and carbamazepine, respectively, at pH 5 and catalyst amount of $1 \text{ g} \cdot \text{L}^{-1}$. The products of ozonation are investigated with a specific ultraviolet absorption at 254 nm. The wide application of metal oxide catalysts in ozone decomposition necessitated the use of different instrumental methods for analysis. Based on the results of X-ray diffraction, X-ray photoelectron spectroscopy, EPR and TPD, it was found that during the destruction of ozone on silver catalyst supported on silica, the silver was oxidized to a complex mixture of Ag_2O and AgO (Naydenov *et al.*, 2008). This investigation of catalytic ozone decomposition on Ag/ SiO_2 was carried out in the temperature range from -40°C to $+25^\circ\text{C}$, it was determined first order of reaction, and the calculated activation energy was $65 \text{ kJ} \cdot \text{mol}^{-1}$. X-ray diffraction was also used to determine the phase composition of manganese oxide catalysts supported on $\gamma\text{-Al}_2\text{O}_3$ and SiO_2 (Buciuman *et al.*, 1998). Moreover, the samples were characterized by Raman and IR spectroscopy. The supported catalysts were prepared by nitrate precursors using the impregnation method. In addition to the Raman spectral bands of $\beta\text{-MnO}_2$ and $\alpha\text{-Mn}_2\text{O}_3$ phases, other signals were also registered and attributed to isolated Mn^{2+} ions present in

Table 6. Comparison of the specific surface areas, the size of metal particles and the average rates of ozone decomposition in water over palladium-containing catalysts.

Catalyst	Specific surface area ($\text{m}^2 \cdot \text{g}^{-1}$)	Size of metal particle (\AA)	Average rate ($\text{mg}_{(\text{O}_3)} \text{min}^{-1} \cdot \text{g}^{-1}_{(\text{cat.})}$)
Pd/ SiO_2	206	90	0.77
Pd/ $\text{SiO}_2 \cdot \text{Al}_2\text{O}_3$	221	70	0.54
Pd/ Al_2O_3	139	75	0.39
Pd/ TiO_2	34	109	0.35

Table 7. Possible mechanisms of catalytic ozone decomposition in water (Lin *et al.*, 2002).

Case of O_2 not adsorbed on metal	Case of O_2 adsorbed on metal
$\text{O}_3 \rightarrow \text{O}_{3(\text{a})}$	$\text{O}_3 \rightarrow \text{O}_{3(\text{a})}$
$\text{O}_{3(\text{a})} \rightarrow \text{O}_{(\text{a})} + \text{O}_2$	$\text{O}_{3(\text{a})} \rightarrow \text{O}_{(\text{a})} + \text{O}_{2(\text{a})}$
$\text{O}_{(\text{a})} + \text{O}_3 \rightarrow 2\text{O}_2$	$\text{O}_{(\text{a})} + \text{O}_3 \rightarrow \text{O}_2 + \text{O}_{2(\text{a})}$ $\text{O}_{2(\text{a})} \rightarrow \text{O}_2$


tetraedrical vacancies on the support surface and in some epitaxial layers, respectively on γ - Mn_2O_3 and manganese silicate. The data from the IR spectra were not very useful due to the fact that the supporter band overlapped the bands of manganese particles formed on the surface and made it difficult to identify them.

Eynaga and Futamura (2005) carried out catalytic oxidation of cyclohexane with ozone on manganese oxide supported on aluminum oxide at the temperature of 295 K. It was performed "in situ" IR studies for taking information on the intermediates formed on the catalytic surface at the time of oxidation. The intermediates were partially oxidized alcohols, ketones, acid anhydrides and carboxylic acids. These compounds were subsequently decomposed by ozone. In the beginning, the activity of the catalyst gradually decreased, whereupon it reached a steady state with mole fractions of CO and CO_2 of respective 90% and 10%. High resistant particles containing C=O, COO- and CH groups remained on the catalyst surface, causing slow deactivation of the catalyst. The C=O groups were decomposed at relatively low temperatures (<473 K), while the COO- and CH groups were dissociated at temperatures > 473 K.

The kinetics of gas-phase ozone decomposition was studied by heterogeneous interactions of ozone with aluminum thin films (Sullivan *et al.*, 2004). The ozone concentrations were monitored in real time using UV absorption spectroscopy at 254 nm. The films were prepared by dispersion of fine alumina powder in methanol, and their specific surface areas were determined by "in situ" adsorption of krypton at 77 K. The reactivity of alumina decreased with increasing ozone concentration. As a consequence of multiple exposures to ozone of one film, the number of active sites was greater than 1.4×10^{14} per cm^2 surface or comparable with the total number of active sites. The coefficients of ozone decomposition were calculated (γ) depending on the initial concentration of ozone in the reaction cell, using the expression:

$$\gamma = (4 \times k^1 \times V) / (c \times SA) \quad (26)$$

where c is the average velocity of gas phase molecules of ozone, k^1 is the observed initial rate constant of ozone decomposition from first order (for the first 10 s), SA is the total surface area of the aluminum film, and V is volume of the reactor. The results indicate that the coefficients of ozone decomposition on fresh films depend inversely on ozone concentration, ranging from 10^{-6} to ozone concentration of 10^{14} molecules per cm^3 to 10^{-5} for 10^{13} molecules per cm^3 ozone. The coefficients of ozone decomposition were found not to depend on the relative humidity of gas stream. The mechanism of the reaction of catalytic ozone decomposition based on detailed spectroscopic investigations of the catalytic surface was discussed (Li *et al.*, 1998; Li & Oyama, 1998), with evidence for the formation of peroxide particles on the surface:



It has been suggested that molecular oxygen could also be initiated by the reaction:



The reactivity of the oxidized aluminum film can be partially restored after being placed for a certain period in a medium free of ozone, water vapor and carbon dioxide.

3.2.2. Decomposition of ozone on the surface of the carbon fiber and inert materials

The use of carbon material in adsorption and catalysis is related to their structural properties and surface chemical groups. Their structural properties are determined by the specific surface area and porosity, while the chemical groups on the surface of the catalyst are composed mainly of oxygen-containing functional groups. Ozone reacts with various carbon materials such as activated carbon, carbon black, graphite, carbon fiber, *etc.* The character of these interactions depends both on the nature of the carbon surface and temperature (Atale *et al.*, 1995). It has been tested two. Two types of interactions were tested: complete oxidation leading to formation of gaseous carbon oxides and partial oxidation producing surface oxygen-containing functional groups (Atale *et al.*, 1995; Mori *et al.*, 1993). With increase of temperature, the ratio between these two processes is displaced in the direction of complete oxidation. The latter is accompanied by an oxidative destruction on the surface with formation of gaseous carbon oxides. In addition, on the surface of the carbon catalytic decomposition of ozone takes place. A number of publications (Kobayashi *et al.*, 1989; Rakitskaya *et al.*, 1994; Aktyacheva & Emelyanova, 1990; Valdes *et al.*, 2002) studied the physicochemical properties of activated carbon treated with ozone, as well as and the kinetics of the process related to the release of CO and CO_2 . Subrahmanyam *et al.* (2005) have examined the catalytic decomposition of ozone to molecular oxygen on active carbon in the form of granules and fibers at room temperature. The dynamics of the activity of the carbons was characterized by two distinct zones. The first one is the observed high activity with respect to the decomposition of ozone, which is mainly due to the chemical reaction of ozone with carbon. As a result of this interaction on the carbons, oxygen-containing surface groups are formed. Then a sharp drop of the conversion is registered and transition of the catalyst to a low active zone takes place. In this zone, the decomposition of the ozone to molecular oxygen proceeds in a catalytic way. The activities of the carbons in dry environment on the one hand and in the presence of water vapor and NO_x on the other were compared. The presence of water vapor reduced the catalytic activity, while the presence of the NO_x improved the activity due to the change in the carbon surface functional groups.

They can be modified in two ways: boiling in dilute nitric acid or thermal treatment at 1273 K in helium media. Positive results were obtained only in the first treatment. The decomposition of ozone with respect to the gasification of carbon with forming of CO_x proceeds


with a selectivity of less than 25%. The catalysts were characterized by means of temperature-programed decomposition of surface functional groups, IR and X-ray photo-electron spectroscopy. The mechanism of decomposition of ozone on activated carbon has been proposed (Figure 6).

In the ozone decomposition process it is difficult to draw a line between relatively inert materials and heterogeneous catalysts. However the separation can be made on the basis of two evident signs: 1) the catalysts for ozone decomposition are specifically synthesized and 2) they have higher catalytic activity (higher values for the coefficient of decomposition γ) compared to the inert materials. In the literature there are investigations on the reaction of ozone destruction on the surface of silica (Tkalic *et al.*, 1984), glass (Olshina *et al.*, 1979), volcanic aerosols (Popovich *et al.*, 1987; Popovich, 1988) and ammonium hydrogen sulfate (Egorova *et al.*, 1988). The published values for the coefficient of ozone decomposition γ for quartz and glass are in the order of $(1-2) \times 10^{-11}$, and those for aerosols and ammonium sulphate—from 1.61×10^{-6} to 7.71×10^{-8} . It is interesting to note the studies of ozone decomposition on the surface of Saharan dust (Hanisch & Crowley, 2002) as well as the application of slurry treated water as catalyst for ozone destruction in aqueous medium (Muruganadham *et al.*, 2007).

The heterogeneous reaction between O_3 and authentic Saharan dust surfaces (Hanisch & Crowley, 2002) was investigated in a Knudsen reactor at ~ 296 K. O_3 was destroyed on the dust surface and O_2 was formed with conversion efficiencies of 1.0 and 1.3 molecules O_2 per O_3 molecule destroyed for unheated and heated samples, respectively. No O_3 desorbed from exposed dust samples, showing that the uptake was irreversible. The uptake coefficients for the irreversible destruction of O_3 on (unheated) Saharan dust surfaces depended on the O_3 concentration and varied between 4.8×10^{-5} and 2.2×10^{-6} for the steady-state uptake coefficient. At very high O_3 concentrations the surface was deactivated, and O_3 uptake ceased after a certain exposure period.


A new, effective and stable ecological catalyst based on slurry (Muruganadham *et al.*, 2007) was used in the process of ozone decomposition in water acidic medium. The catalyst was characterized by X-ray fluorescence, transmission electron microscopy, scanning electron microscopy and X-ray diffraction. The sludge is essentially composed of different metallic and non-metallic oxides. The effect of various experimental parameters was investigated, including catalyst amount, initial ozone concentration and application of different metal oxide catalysts. The decomposition of dissolved ozone is significantly increased with the enhancement of the initial ozone concentration and the increment of catalyst amount from 125 to 750 mg. The order of activity of the catalysts tested was as follows: $ZnO \approx \text{sludge} > TiO_2 > SiO_2 > Al_2O_3 \approx Fe_2O_3$. Ozone did not affect the catalyst morphology and its composition and it is concluded that sludge is a promising catalyst for ozone decomposition in water.

Region of high activity. Chemical reaction of ozone with carbon



Region of low activity. Catalytic decomposition of ozone

I. In the absence of NO_x



II. In the presence of NO_x




Figure 6. Simplified scheme of ozone decomposition on carbon.

On balance of the literature review it can be concluded that except metals of the platinum group, characterized by their high price, the metal oxide catalysts containing manganese oxide have the highest activity in decomposition of gaseous ozone and also in catalytic oxidation of pollutants. It is important to mention that unlike the inert materials, the oxide catalysts do not show strong dependence of catalytic activity on ozone concentration in gas phase. It should be emphasized that despite the great number of publications on the subject, the kinetics and the mechanism of ozone decomposition on the surface of heterogeneous metal oxide catalysts have not yet been cleared up sufficiently.

REFERENCES

- Aktyacheva L, Emelyanova G. (1990). Activated carbon treatment with ozone. *J Phys Chem* **31**: 21 [in Rus].
- Alexandrov YA, Tarunin BI, Perepletchikov ML. (1983). UV absorption of gaseous ozone. *J Phys Chem* **LVIII**(10): 2385–2397 [in Rus].
- Atale S, Hitoshi M, Kaneko N, Taraichi K, Yano M. (1995). Ozone reactions with various carbon materials. *Jap Pat CA*, 123, 121871.
- Baldi M, Finocchio E, Pistarino C, Busca G. (1998). Evaluation of the mechanism of the oxy-dehydrogenation of propane over manganese oxide. *J Appl Catal A: General* **173**: 61–74.
- Baltanas MA, Stiles AB, Katzer JR. (1986). Development of supported manganese oxides catalysts for partial oxidation: Preparation and hydrogenation properties. *Appl Catal* **28**: 13–33.
- Becker KH, Schurath U, Seitz H. (1974). Ozone-olefin reactions in the gas phase 1. Rate constants and activation energies. *Int J Chem Kinet* **6**(5) 725–739.
- Bianchi CL, Pirola C, Ragaini V, Selli E. (2006). Mechanism and efficiency of atrazine degradation under combined oxidation processes. *Appl Catal B Environ* **64**(1–2): 131–138.
- Boreskov GK. (1965). The catalysis of isotopic exchange in molecular oxygen. *Adv Catal* **15**: 285–339.
- Brown TL, Le May HE Jr, Bursten BE, Burdige JR. (2002). *Chemistry: The Central Science, Ninth edition*, Prentice Hall, New Jersey.
- Buciuman F, Patcas F, Craciun R, Zhan DRT. (1998). Vibrational spectroscopy of bulk and supported manganese oxides. *Phys Chem Chem Phys* **1**: 185–190.
- Chapman S. (1930a). On ozone and atomic oxygen in the upper atmosphere. *Phil Mag* **10**: 369–383.
- Chapman S. (1930b). A theory of upper-atmospheric ozone. *Mem Roy Meteor Soc* **3**: 103–125.

- Che M, Tench AJ. (1982). Characterization and reactivity of mononuclear oxygen species on oxide surfaces. *Adv Catal* **31**: 77–133.
- Claudia C, Mincione E, Saladino R, Nicoletti R. (1994). Oxidation of substituted 2-thiouracils and pyrimidine-2-thione with ozone and 3,3-dimethyl-1,2-dioxirane. *Tetrahedron* **50**(10): 3259–3272.
- Crutzen PJ, Schmalzl U. (1983). Chemical budgets of the stratosphere. *Planet Space Sci* **31**: 1009–1032.
- DeMore WB, Raper O. (1964). Hartley and extinction coefficients of ozone in the gas phase and in liquid nitrogen, carbon monoxide, and argon. *J Phys Chem* **68**(2): 412–414.
- Deninno MP, McCarthy KE. (1997). The C-14 radiolabeled synthesis of the cholesterol absorption inhibitor cp-148,623 – A novel method for the incorporation of a C-14 label in enones. *Tetrahedron* **53**(32): 11007–11020.
- Dhandapani B, Oyama ST. (1997). Gas phase ozone decomposition catalysts. *J Appl Catal B: Environ* **11**(2): 129–166.
- Egorova GV, Popovich MP, Filipov YuV. (1988). Ozone destruction on the surface of ammonium hydrogen sulfate. *J Phys Chem* **29**(4): 406–413 [in Russian].
- Einaga H, Futamura S. (2004). Comparative study on the catalytic activities of alumina-supported metal oxides for oxidation of benzene and cyclohexane with ozone. *React Kinet Catal Lett* **81**(1): 121–128.
- Einaga H, Futamura S. (2005). Oxidation behavior of cyclohexane on alumina-supported manganese oxide with ozone. *J Appl Catal B: Environ* **60**(1–2): 49–55.
- Einaga H, Harada M, Futamura S. (2005). Structural changes in alumina-supported manganese oxides during ozone decomposition. *Chem Phys Lett* **408**(4–6): 377.
- Einaga H, Ogata A. (2009). Benzene oxidation with ozone over supported manganese oxide catalysts: Effect of catalyst support and reaction conditions. *J Hazard Mater*. **164**(2–3): 1236–1241.
- Ellis WD, Tomets PV. (1972). Room-temperature catalytic decomposition of ozone. *Atmospheric Environment* **6**(10): 707–714.
- Emelyanova G, Lebedev V, Kobozev N. (1964). Catalytic activity of noble metals in ozone destruction. *J Phys Chem* **38**: 170–180 [in Russian].
- Emelyanova G, Lebedev V, Kobozev N. (1965). Ozone decomposition kinetics. *J Phys Chem* **39**: 540–548 [in Russian].
- Emelyanova G, Strakhov B. (1968). Activity of NiO in ozone decomposition reaction. *Adv Probl Phys Chem* **2**: 149–158 [in Russian].
- Farmen J, Gardiner B, Shanklin J. (1985). Large losses of total ozone in Antarctica reveal seasonal ClOx/NOx interaction. *Nature* **315**: 207–210.
- Galimova LG, Komisarov VD, Denisov ET. (1973). Ozonation of phenol. *Rep Rus Acad Sci* **2**: 307–317 [in Russian].
- Gerchenson Yu, Zvenigorodskii S, Rozenstein V. (1990). Role of ozone for the greenhouse effect. *Success Chemistry*. **59**: 1601–1609 [in Russian].
- Griggs M. (1968). Absorption coefficients of ozone in the ultraviolet and visible regions. *J Chem Phys* **49**(2): 857–859.
- Hanisch F, Crowley JN. (2002). Ozone decomposition on Saharan dust: an experimental investigation. *Atmos Chem Phys Discuss* **2**: 1809–1845.
- Hata K, Horiuchi M, Takasaki T. (1988). Preparation of high performance metal catalyst. Jap Pat CA, 108, 61754u.
- Hata K, Horiuchi M, Takasaki K, Ichihara S. (1987). Special technology for synthesis of catalysts. Jap Pat 62,201,648, Sep 5, to Nippon Shokubai Kagaku Kogyo Co., Ltd.
- Heisig C, Zhang W, Oyama ST. (1997). Decomposition of Ozone using Carbon Supported Metal Oxide Catalysts. *J Appl Catal B: Environ* **14**(1–2): 117–129.
- Hon YS, Yan JL. (1993). The ozonolytic cleavage of cycloalkenes in the presence of methyl pyruvate to yield the terminally differentiated compounds. *Tetrahedron Lett* **34**(41): 6591–6594.
- Houzellot JZ, Villiermaux J. (1976). Étude d'une cinétique de décomposition hétérogène... sur oxyde de nickel. *J de Chimie Physique* **73**(7–8): 807–812.
- Hunter P, Oyama ST. (2000). *Control of Volatile Organic Compound Emissions: Conventional and Emerging Technologies*, John Wiley & Sons, Inc.
- Imamura S, Ikebata M, Ito T, Ogita T. (1991). Decomposition of ozone on a silver catalyst. *Ind Eng Chem Res* **30**(1): 217–221.
- Inn ECJ, Tanaka VJ. (1953). Absorption coefficient of ozone in the ultraviolet and visible regions. *Opt Soc Amer* **43**(10): 870–872.
- Johnston HS. (1975). Global ozone balance in the natural stratosphere. *Rev Geoph* **13**(5): 637–649.
- Kapteijn F, Singoredjo L, Andreini A, Moulijn JA. (1994). Activity and selectivity of pure manganese oxides in the selective catalytic reduction of nitric oxide with ammonia. *J Appl Catal B: Environ* **3**(2–3): 173–189.
- Kashtanov L, Ivanova N, Rizhov B. (1936). Catalytic activity of metals in ozone decomposition. *J Applied Chemistry* **9**: 2176–2182 [in Russian].
- Kobayashi M, Mitsui K. (1988). Development for synthesis of zinc oxide. Jap. Pat. 63,267,439, Nov 4, to Nippon Shokubai Kagaku Kogyo Co., Ltd.
- Kobayashi M, Mitsui M, Kiichiro K. (1988). Chemical composition of metal oxide catalysts. Jap Pat, CA, 109, 175615a.
- Kobayashi M, Motonobu S, Mitsui M, Kiichiro K. (1989). Ozone decomposition on Pt/SiO₂ catalyst. Jap Pat, CA, 110, 120511d.
- Kondratev K. (1989). Ozone reaction with OH radicals. *Meteorology and Climate*. **19**: 212–218 [in Russian].
- Kondratev K. (1990). Ozonolysis of β-cyclodextrin. *Success Chemistry* **59**: 1587–1598 [in Russian].
- Konova P, Stoyanova M, Naydenov A, Christoskova ST, Mehandjiev D. (2006). Catalytic oxidation of VOCs and CO by ozone over alumina supported cobalt oxide. *J Appl Catal A: Gen* **298**: 109–114.
- Kutsuna S, Kasuda M, Ibusuki T. (1994). Transformation and decomposition of 1,1,1-trichloroethane on titanium dioxide in the dark and under photoillumination. *Atmospheric Environment* **28**(9): 1627–1631.
- Kuwabara H, Fujita H. (1991). Highly specific surface ZrO₂ for ozone destruction. Jap Pat 3016640, Jan 24, to Mitsubishi Heavy Industries, Ltd.
- Li W, Gibbs GV, Oyama ST. (1998). Mechanism of ozone decomposition on manganese oxide: 1. In situ laser Raman spectroscopy and ab initio molecular orbital calculations. *J Am Chem Soc* **120**(35): 9041–9046.
- Li W, Oyama ST. (1996). Catalytic methane oxidation at low temperatures using ozone, in *Heterogeneous Hydrocarbon Oxidation (Acs Symposium Series)* (Warren BK and Oyama ST eds) pp. 364–373, ACS: Washington, DC.
- Li W, Oyama ST. (1998). The mechanism of ozone decomposition on manganese oxide: 2. Steady-state and transient kinetic studies. *J Am Chem Soc* **120**(35): 9047–9052.
- Lin J, Kawai A, Nakajima T. (2002). Effective Catalysts for Decomposition of Aqueous Ozone. *J Appl Catal B: Environ* **39**(2): 157–165.
- Lo Jacono M, Schiavello M. (1976). The influence of preparation methods on structural and catalytic properties of transition metal ions supported on alumina. *Studies in Surface Science and Catalysis* **1**: 473–487.
- Lunin VV, Popovich MP, Tkachenko SN. (1998). Physical chemistry of ozone. Moscow State University Publisher, 480 p. [in Russian].
- Ma J, Chuah GK, Jaenicke S, Gopalakrishnan R, Tan KL. (1995). Catalysis by manganese oxide monolayers. Part 1: Alumina and magnesia supports. *Berichte der Bunsengesellschaft für physikalische Chemie* **99**(2): 184–195.
- Ma J, Chuah GK, Jaenicke S, Gopalakrishnan R, Tan KL. (1995). Catalysis by manganese oxide monolayers. Part 2: Zirconia support. *Berichte der Bunsengesellschaft für physikalische Chemie* **100**(5): 585–593.
- Ma J, Sui MH, Chen ZL, Li NW. (2004). Degradation of refractory organic pollutants by catalytic ozonation – activated carbon and Mn-loaded activated carbon as catalysts. *Ozone Sci Eng* **26**(1): 3–10.
- Maltha A, Favre LFT, Kist HF, Zuur AP, Ponc V. (1994). Manganese oxides as catalysts for the selective reduction of nitrobenzene to nitrosobenzene. *J Catal* **149**(2): 364–374.
- Martinov I, Demiduk V, Tkachenko S, Popovich M. (1994). Influence of the CuO and CoO on the process of ozone decomposition. *J Phys Chem* **68**: 1972–1980 [in Rus].
- Martinov IV, Tkachenko SN, Demidyuk VI, Egorova GV, Lunin VV. (1999). NiO Addition Influence over Cement-containing Catalysts Activity in Ozone Decomposition. *J Moscow Univ, Ser. 2: Chemistry* **40**: 355–361 [in Rus].
- Monchot W, Kampschulte W. (1907). Über die Einwirkung von Ozon auf metallisches Silber und Quecksilber. *Berichte der deutschen chemischen Gesellschaft* **40**(3): 2891.
- Mori, Katsushiko, Hasimoto, Akira. (1993). Partial carbon oxidation by ozone. Jap. Pat., CA, 118, 153488v.
- Muruganadham M, Chen SH, Wu JJ. (2007). Evaluation of water treatment sludge as a catalyst for aqueous ozone decomposition. *Catal Commun* **8**(11): 1609–1614.
- Naydenov A, Konova P, Nikolov P, Klingstedt F, Kumar N, Kovacheva D, Stefanov P, Stoyanova R, Mehandjiev D. (2008). Decomposition of ozone on Ag/SiO₂ catalyst for abatement of waste gases emissions. *Catal Today* **137**(2–4): 471–474.

- Naydenov A, Mehandjiev D. (1993). Complete oxidation of benzene on manganese dioxide by ozone. *J Appl Catal A: Gen* **9**(1): 17–22.
- Naydenov A, Stoyanova R, Mehandjiev D. (1995). Ozone decomposition and CO oxidation on CeO₂. *J Mol Catal A: Chem* **98**(1): 9–14.
- Olszyna K, Cadle RD, dePena RG. (1979). Stratospheric heterogeneous decomposition of ozone. *J Geophys Res: Oceans* **84**(C4): 1771–1775.
- Oohachi K, Fukutake T, Sunao T. (1993). Method for synthesis of iron oxides, Jap Pat, CA, 119, 119194g.
- Oyama ST. (2000). Chemical and catalytic properties of ozone. *Catal Rev Sci Eng* **42**(3): 279–322.
- Perry RH, Green D. (1997). *Perry's chemical engineer's handbook*, McGraw-Hill Professional, New York.
- Popovich M. (1988). Influence of the SiO in ozone decomposition reaction. *J Phys Chem* **29**(5): 427–434 [in Russian].
- Popovich M. (1988). Investigation on ozone destruction over volcanic aerosols, *J. Moscow Univ, Ser Chem* **29**: 29–35 [in Russian].
- Popovich MP, Smirnova NN, Sabitova LV. (1987). Influence of Na content on the volcanic aerosols activity in ozone decomposition. *J Phys Chem* **28**(6): 548–557 [in Russian].
- Popovich M, Smirnova N, Sabitova L, Filipov Yu. (1985). Catalytic properties of copper oxide. *J. Moscow Univ, Ser Chem* **26**: 167–177 [in Russian].
- Qi F, Chen Z, Xu B, Shen J, Ma J, Joll C, Heitz A. (2008). Influence of surface texture and acid-base properties on ozone decomposition catalyzed by aluminum (hydroxyl) oxides. *Appl Catal B: Environ* **84**(3–4): 684–690.
- Radhakrishnan R, Oyama ST, Chen J, Asakura A. (2001). Electron Transfer Effects in Ozone Decomposition on Supported Manganese Oxide. *J Phys Chem B* **105**(19): 4245–4253.
- Rakitskaya TL, Bandurko AY, Ennan AA, Paina VY, Rakitskiy AS. (2001). Carbon-fibrous-material-supported base catalysts of ozone decomposition. *Micropor Mesopor Mat* **43**(2): 153–160.
- Rakitskaya TL, Vasileva EK, Bandurko AY, Paina VY. (1994). Kinetics of Ozone Decomposition on Activated Carbons, *Kinetics and Catalysis* **35**(1): 90–92.
- Rakovsky S, Nenchev L, Cherneva D. (1979). Decomposition of ozone in presence of NiO, in *Proc. 4th Symp. Heterogeneous Catalysis*, Varna, p. 231.
- Rakovsky SK, Zaikov GE. (2007). *Kinetic and mechanism of ozone reactions with organic and polymeric compounds in liquid phase – 2nd edition*, Nova Sci. Publ., Inc. New York.
- Razumovskii SD, Rakovsky SK, Shopov DM, Zaikov GE. (1983). *Ozone and its reactions with organic compounds*. Publ. House of Bulgarian Academy of Sciences, Sofia, 287 p. [in Russian].
- Razumovskii SD, Zaikov GE. (1974). *Ozone and its reactions with organic compounds*, Moscow [in Russian].
- Rosal R, Rodriguez A, Gonzalo MS, Garcia-Calvo E. (2008). Catalytic ozonation of naproxen and carbamazepin on titanium dioxide. *Appl Catal B: Environ* **84**(1–2): 48–57.
- Rubashov AM, Pogorelov VV, Strahov BV. (1972). Catalytic activity of Fe₂O₃ in decomposition of ozone. *J Phys Chem* **46**(9): 2283–2291 [in Russian].
- Rubashov AM, Strahov BV. (1973). Formation of oxygen species on Fe₂O₃ surface during ozonation. *J Phys Chem* **47**(8): 2115–2122 [in Russian].
- Schönbein CF. (1840). On the odour accompanying electricity and on the probability of its dependence on the presence of a new substance. *Philosophical Magazine* **17**: 293–294.
- Schwab G, Hartman C. (1964). Metal catalysts for decomposition of ozone. *J Phys Chem* **6**: 72–86 [in Russian].
- Skoumal M, Cabot PL, Centellas F, Arias C, Rodriguez RM, Garrido JA, Brillas E. (2006). Mineralization of paracetamol by ozonation catalyzed with Fe²⁺, Cu²⁺ and UVA light. *Appl Catal B: Environ* **66**(3–4): 228–240.
- Solomon S, Garcia RR, Rowland F, Wuebbles P. (1986). Regeneration rates of the stratospheric ozone. *Nature* **321**: 755–758.
- Stoyanova M, Konova P, Nikolov P, Naydenov A, Christoskova ST, Mehandjiev D. (2006). Alumina-supported nickel oxide for ozone decomposition and catalytic ozonation of CO and VOCs. *Chem Eng J* **122**(1–2): 41–46.
- Subrahmanyam C, Bulushev DA, Kiwi-Minsker L. (2005). Dynamic behaviour of activated carbon catalysts during ozone decomposition at room temperature. *Appl Catal B: Environ* **61**(1–2): 98–106.
- Subrahmanyam C, Renken A, Kiwi-Minsker L. (2007). Novel catalytic non-thermal plasma reactor for the abatement of VOCs. *Chem Eng J* **134**(1–3): 78–83.
- Sudak A, Volfson V. (1983). Catalytic Method of Removing Ozone Impurities from Air. The Role of Chemistry in Preserving the Environment. *Scientific Notion*, Kiev, 87–100 [in Russian].
- Sullivan RC, Thornberry T, Abbatt JPD. (2004). Ozone decomposition kinetics on alumina: Effects of ozone partial pressure, relative humidity and repeated oxidation cycles. *Atmos Chem Phys* **4**: 1301–1310.
- Tanaka V, Inn ECJ, Watanabe KJ. (1953). Absorption coefficients of gases in the vacuum ultraviolet. Part IV. Ozone. *J Chem Phys* **21**(10): 1651–1654.
- Tarunin BI, Perepletchikov ML, Klimova MN. (1981). Kinetics of decomposition of ozone in gradient-free reactor. *Kinetics and Catalysis* **22**(2): 431–442 [in Russian].
- Taube H. (1957). Photochemical reactions of ozone in solution. *Trans Faraday Soc* **53**: 656–665.
- Tchihara S. (1988). Co-catalyst for decomposition of ozone. Jap Pat, CA, 108, 192035h.
- Tench AJ, Lawson T. (1971). The formation of O⁻ and O₃⁻ adsorbed on an oxide surface. *Chem Phys Lett* **7**(4): 459–460.
- Terui S, Miyoshi K, Yokota Y, Inoue A. (1990). Experimental method for ozone decomposition on silver oxide catalyst, Jap Pat 02,63,552, Mar 2.
- Terui S, Sadao K, Sano N, Nichikawa T. (1990). Synthesis of supported silver oxide catalysts, Jap Pat, CA, 112, 20404p.
- Terui S, Sadao K, Sano N, Nichikawa T. (1991). Investigation on Pd and Rh catalysts supported on colloidal polyurethane for ozone destruction, Jap Pat, CA, 114, 108179b.
- Thorp CE. (1955). *Bibliography of Ozone Technology Volume 2: Physical and Pharmacological Properties*, Armour Research.
- Tkalich VS, Klimovskii AO, Lissachenko AA. (1984). Study of heterogeneous reactions of ozone. Experimental installation and method. *Kinetics and Catalysis* **25**(5): 1109–1116 [in Russian].
- Tong S, Liu W, Leng W, Zhang Q. (2003). Characteristics of MnO₂ catalytic ozonation of sulfosalicylic acid propionic acid in water. *Chemosphere* **50**(10): 1359–64.
- Valdes H, Sanches-Polo M, Rivera-Utrilla J, Zaror CA. (2002). Effect of ozone treatment on surface properties of activated carbon, *Langmuir*, **18**, 2111.
- Von Gunten U. (2003). Ozonation of drinking water: Part I. Oxidation kinetics and product formation, *Water Res.*, **37**, 1443–1463.
- Vupputuri R. (1988). Optical properties of stratospheric ozone, *Atm. Environ.*, **22**, 2809.
- Watson RT, Geller MA, Stolarski RS, Hampson RF, United States – Office Of Space Science And Applications – Earth Science And Applications Division. (1986). Present state of knowledge of the upper atmosphere : an assessment report: processes that control ozone and other climatically important trace gases. *NASA Reference Publication Nr. 1162*, NASA, Scientific and Technical Information Branch; Springfield, VA.
- Wiley-VCH. (1991). *Ullmann's Encyclopedia of Industrial Chemistry*. John Wiley and Sons, New York.
- Yamashita T, Vannice A. (1996). N₂O Decomposition over Manganese Oxides, *J Catalysis* **161**(1): 254–262.
- Yoshimoto M, Nakatsuji T, Nagano K, Yoshida K. (1990). Pd-catalyzed ozonation of aqueous phenol solution, Eur. Pat. 90,302,545.0, Sep 19, to Sakai Chemical Industry Co., Ltd.
- Zavadskii AV, Kireev SG, Muhin VM, Tkachenko SN, Chebkin VV, Klushin VN, Teplyakov DE. (2002). Effect of thermal treatment on the activity of hopcalite in ozone decomposition. *J Phys Chem* **76**: 2072–2074 [in Russian].
- Zhao L, Ma J, Sun ZZ. (2008). Oxidation products and pathway of ceramic honeycomb-catalyzed ozonation for the degradation of nitrobenzene in aqueous solution. *Appl Catal B: Environ* **79**(3): 244–253.